



## Tairyfil Carbon Fiber Specification

Test Method : JIS-7608

Product		TC-35	
Filament Count		6K	
Unit		(English)	(SI)
Tensile Strength	Max	NA	NA
	Average	580Ksi	4,000MPa
	Min	530Ksi	3,657MPa
Tensile Modulus	Max	NA	NA
	Average	35.0Msi	240GPa
	Min	34.0Msi	234GPa
Yield (Line density)	Max	-	414 g/1000m
	Average	-	400 g/1000m
	Min	-	386 g/1000m
Elongation		1.60~1.80%	
Sizing Type		Epoxy*	
Sizing content Wt%		0.8~1.4 %	
Bobbin Weight		2kg	

\* Compatible resin matrix: Epoxy, Vinyl Ester, BMI

\*2012.05